

WELDING

ZINC-RICH GALVANIZING COMPOUND



WL™ 740

PREVENTS CORROSION

Corrosion preventative

MAX TEMP
600°F/
316°C

Maximum operational temperature:
600 °F (316 °C)

92%
Zn
DRY FILM

92% Zinc in dry film

H 2
F 2
R 1

HMIS Hazard Rating:
Health (2) • Flammability (2) • Reactivity (1)

- Low VOC*
- 97% pure zinc dust
- Meets MIL-P-26915D
- Non-sagging
- Stops rust
- Covers in one coat



PRESERVE. PROTECT. PREVENT.™

Sprayon® WL™ 740 Zinc-Rich Galvanizing Compound is a high performance primer containing 97% pure zinc dust pigment blended with epoxy resin. Stops rust by electro-chemical action on steel or galvanized coatings. The self-sacrificing zinc protects the base metal, preserving strength and prevents rust creepage when the area is penetrated or scratched. This compound fuses zinc to the metal substrate and delivers protection against corrosion equal to or better than hot dipped galvanize.

