

Performance Data – Pull-Out and Shear Testing in 3,323 PSI Concrete

Average Pull-Out		Shear Values	
Embedment	Pounds	Embedment	Pounds
1"	813	1"	1,302
1-3/4"	1,488	1-3/4"	2,260